

## Technical data sheet

# evguard<sup>®</sup> Design Black opaque 9005

EVA interlayer for design glass in indoor applications

DESIGNED,  
DEVELOPED  
AND MADE  
IN GERMANY




### Processing

Minimum temperature	105 °C (220 F)
Maximum temperature	160 °C (320 F)
Production process	Vacuum



### Dimensions & Packaging

Thickness	min. 0.2 mm, max. 1.14 mm	Customized dimensions and packaging on individual request
Width	min. 800 mm, max. 2,400 mm	
Core	76 mm cardboard core	
Packaging	in cardboard boxes	



### Properties

	Test method	non cross-linked	cross-linked*
Density	ISO 1183	0.95–0.99 g/cm <sup>3</sup>	
Optical appearance		black opaque matt	black opaque
Tensile strength	ISO 527-3	MD > 3 N/mm <sup>2</sup>	MD > 10 N/mm <sup>2</sup>
		CD > 3 N/mm <sup>2</sup>	CD > 10 N/mm <sup>2</sup>



### Storage recommendation

Temperature	< 30 °C (85 F)
Humidity	< 80 %
Shelf life	use by 12 months after date of production Opened rolls have to be protected against direct sunlight and dust.



**Folienwerk Wolfen GmbH**  
Guardianstraße 4  
06766 Bitterfeld-Wolfen  
Germany

T +49 (0)3494 6979 0  
F +49 (0)3494 6979 37  
info@folienwerk-wolfen.de  
www.folienwerk-wolfen.de



[www.evguard.de/en](http://www.evguard.de/en)

#### Disclaimer

Our information about our products and processes is based on extensive research and our considerable experience in the field of applied engineering. We provide this information, which to the best of our knowledge is correct, orally and in writing. In doing so, we do not assume any liability other than the liability agreed upon in the respective individual contract, and we reserve the right to make technical modifications in the course of our product development. However, this shall not release user from its obligation to verify the suitability of our products and processes for its own use. Purchaser's specifications of intended use shall only be binding, if we, at the time of contract conclusion, have confirmed in writing that the delivered goods are suitable for the use intended by Purchaser. This shall also apply to the protection of third party industrial property rights and to applications and processes.