

Ficha técnica

Evguard® Design Blanco Opaco



DESIGNED,
DEVELOPED
AND MADE
IN GERMANY



Proceso

Temperatura mínima	105 °C (220 F)
Temperatura máxima	160 °C (320 F)
Proceso de producción	Vacio



Dimensión y Embalaje

Espesor	min. 0.2 mm, max. 1.14 mm	Dimensiones y embalaje personalizados bajo pedido individual.
Ancho	min. 800 mm, max. 2,400 mm	
Núcleo	76 mm Núcleo de carton	
Packaging	Cajas de cartón	



Propiedades Método de prueba si n cross-linked cross-linked*

Propiedades	Método de prueba	si n cross-linked	cross-linked*
Densidad	ISO 11	0.95 – 0.99 g/cm ³	
Apariencia óptica		Blanco opaco mate	Blanco opaco
Tensión	ISO 527-3	MD > 3 N/mm ²	MD > 10 N/mm ²
		CD > 3 N/mm ²	CD > 10 N/mm ²



Recomendación de almacenaje

Temperatura	< 30 °C (85 F)
Humedad	< 80 %
Vida útil	12 meses después de la fecha de fabricación. Los rollos abiertos deben protegerse contra la luz solar directa y el polvo.



Folienwerk Wolfen GmbH
Guardianstraße 4
06766 Bitterfeld-Wolfen
Germany

T +49 (0)3494 6979 0
F +49 (0)3494 6979 37
info@folienwerk-wolfen.de
www.folienwerk-wolfen.de



www.evguard.de/en

Disclaimer

Our information about our products and processes is based on extensive research and our considerable experience in the field of applied engineering. We provide this information, which to the best of our knowledge is correct, orally and in writing. In doing so, we do not assume any liability other than the liability agreed upon in the respective individual contract, and we reserve the right to make technical modifications in the course of our product development. However, this shall not release user from its obligation to verify the suitability of our products and processes for its own use. Purchaser's specifications of intended use shall only be binding, if we, at the time of contract conclusion, have confirmed in writing that the delivered goods are suitable for the use intended by Purchaser. This shall also apply to the protection of third party industrial property rights and to applications and processes.